

SOY/COCONUT CONTAINER WAX GOLDEN WAX® 454

GENERAL USE GUIDELINES

- ◆ MELTING TEMPERATURE: 175°F (+/-5°F)
- ◆ POUR TEMPERATURE: 160°F (+/-5°F)
- ◆ FRAGRANCE LOAD: 5-10%
- ◆ COOLING: ambient temperature (70-75°F)
- ◆ WAX MELTING POINT: 115-125°F

BENEFITS

may be used alone—no need for paraffin or other non plant-based waxes

single pour

offers bloom/frost reduction

good glass adhesion



Conditions will vary based on mold/container type and size, fragrance and dye used